



Especificaciones técnicas

APP		PG-40 APP	PA-30 APP	PG-45 APP	PA-40 APP	VG-35 APP	VA-30 APP	
Espesor:	(mm)	4.00	3.00	4.50	4.00	3.50	3.00	
Dimensiones del rollo :	(mts)	10.0 X 1.0	10.0 X 1.0	10.0 X 1.0	10.0 X 1.0	10.0 X 1.0	10.0 X 1.0	
Cobertura:	(m ²)	9.00	9.00	9.00	9.00	9.00	9.00	
Peso del rollo:	(kgs)	46.00	36.00	53.00	46.00	42.00	36.00	
Refuerzo:		POLIES-TER 180 grs/m ²	POLIES-TER 180 grs/m ²	POLIES-TER 180 grs/m ²	POLIES-TER 180 grs/m ²	FIBRA DE VIDRIO 90 grs/m ²	FIBRA DE VIDRIO 90 grs/m ²	
Acabado superior:		GRAVILLA	ARENA	GRAVILLA	ARENA	GRAVILLA	ARENA	
Acabado inferior:		POLIETI-LENO	POLIETI-LENO	POLIETI-LENO	POLIETI-LENO	POLIETI-LENO	POLIETI-LENO	
Punto de reblandeci-miento:	(°C)	151	151	151	151	151	151	
Flexibilidad a baja temperatura:	(°C)	-10	-10	-10	-10	-10	-10	
Permeabilidad al vapor:		PASA	PASA	PASA	PASA	PASA	PASA	
Resistencia a la tensión:	LONG	(Lbs/pulg)	100	100	100	100	70	70
	TRANS		70	70	70	70	50	50
Elongación a la ruptura:	LONG	(%)	50	50	50	50	6	6
	TRANS		50	50	50	50	6	6